

## PAGEL®-EPOXY RESIN GROUT

### PROPERTIES

- **Load-bearing after only a few hours**
- **Pourable** epoxy resin grout
- **Pre-mixed** filler with trunk resin and de-aerated in a vacuum
- **Excellent flow behaviour**
- **Watertight**
- **Good adherence** to steel surfaces
- Statically and **dynamically high load-bearing** capacity
- Very high compressive and shear strength
- **Vibration-reducing**
- **Frictional connection**
- Does not need an **adhesion layer** on a normal base and is applied directly to the prepared concrete surface or rust-free steel surface
- **Resistant** to lyes, light acids and mineral oils
- Resistant up to a service temperature of 70°C – high resistance to temperature changes


### FIELDS OF APPLICATION

- Grouting for track plates and ribbed slabs
- Grouting for thin layers
- Grouting for galvanised steel parts and non-ferrous metals
- Grouting for precision bearings
- Grouting for automated warehouse supports
- Grouting for pumps, coagulants and compressors in the chemical industry
- Grouting for noise barrier posts and base plates in road and bridge construction
- Grouting between steel plates

**EH196R**

| CE                                                           |                                                                                        |
|--------------------------------------------------------------|----------------------------------------------------------------------------------------|
| PAGEL® Spezial-Beton GmbH & Co. KG<br>D-45355 Essen          |                                                                                        |
|                                                              | find the printed batch number                                                          |
|                                                              | <b>EN 13813 SR-AR1-B1,5-IR4</b>                                                        |
|                                                              | Epoxy resin grout/coating for indoor use<br>(superstructures according to tech. info): |
| Product fire behaviour:                                      | E <sub>s</sub>                                                                         |
| Release of corrosive substances<br>(Synthetic Resin Sreced): | SR                                                                                     |
| Water permeability:                                          | NPD <sup>1)</sup>                                                                      |
| Abrasion resistance:                                         | AR1 <sup>2)</sup>                                                                      |
| Tensile bond strength:                                       | B 1.5                                                                                  |
| Impact resistance:                                           | IR 4                                                                                   |
| Sound insulation:                                            | NPD                                                                                    |
| Sound absorption:                                            | NPD                                                                                    |
| Thermal insulation:                                          | NPD                                                                                    |
| Resistance to chemicals:                                     | NPD                                                                                    |

1) NPD = No Performance Determined  
2) Refers to coating when smooth and not yet coated with sand



| TECHNICAL DATA                                                                                                                    |        |        |         |
|-----------------------------------------------------------------------------------------------------------------------------------|--------|--------|---------|
| TYPE                                                                                                                              |        | EH196R |         |
| Grain size                                                                                                                        | mm     | 0-0.5  |         |
| Layer thickness                                                                                                                   | mm     | 6-50   |         |
| Mixing ratio                                                                                                                      |        |        |         |
| resin : hardener                                                                                                                  |        | = M:   | 10:1    |
| Density at 23°C/50% r.h. of air                                                                                                   | kg/dm³ | 1.80   |         |
| Slump                                                                                                                             | cm     | ≥ 30   |         |
| Measure of flow                                                                                                                   | cm     | ≥ 60   |         |
| Pot life                                                                                                                          | 10 °C  | min.   | app. 40 |
|                                                                                                                                   | 20 °C  | min.   | app. 30 |
|                                                                                                                                   | 30 °C  | min.   | app. 20 |
| Reworkable                                                                                                                        | 10 °C  | h      | 24-36   |
|                                                                                                                                   | 20 °C  | h      | 10-20   |
|                                                                                                                                   | 30 °C  | h      | 8-15    |
| Minimum processing temperature at the underground                                                                                 |        | °C     | 10      |
| Compressive strength*<br>(at 20 °C)                                                                                               | 5 h    | N/mm²  | ≥ 70    |
|                                                                                                                                   | 8 h    | N/mm²  | ≥ 90    |
|                                                                                                                                   | 1 d    | N/mm²  | ≥ 100   |
|                                                                                                                                   | 7 d    | N/mm²  | ≥ 110   |
|                                                                                                                                   | 10 d   | N/mm²  | ≥ 110   |
| Bending strength<br>(at 20 °C)                                                                                                    | 5 h    | N/mm²  | ≥ 10    |
|                                                                                                                                   | 8 h    | N/mm²  | ≥ 20    |
|                                                                                                                                   | 1 d    | N/mm²  | ≥ 30    |
|                                                                                                                                   | 7 d    | N/mm²  | ≥ 35    |
|                                                                                                                                   | 10 d   | N/mm²  | ≥ 40    |
| Adhesive strength                                                                                                                 | 7 d    | N/mm²  | ≥ 1.5   |
| Elastic modules (static)                                                                                                          | 7 d    | N/mm²  | 13.000  |
| All test data are guide values, proofed in our German manufacturing plants,<br>- values from other manufacturing plants may vary. |        |        |         |

All test data are guide values, proofed in our German manufacturing plants,  
- values from other manufacturing plants may vary.

\* DIN EN 196-1-compliant compressive strength testing

**Storing:** 12 months when kept dry & cool  
in original sealed containers  
**Packaging:** 15 kg containers  
**Hazard category:** See safety data sheet

### PHYSIOLOGICAL BEHAVIOUR AND SAFETY MEASURES

The plastic is harmless when hardened. Read and follow the warning on the container before using. If it comes into contact with skin, clean thoroughly with plenty of water and soap. We recommend reading the BG Data Sheet BGR 227 "Handling Epoxy resins. Do not allow to drain into sewerage systems, open waters or ground soil in an unhardened state. Remove any spilt material immediately using sawdust, for example. Dispose of containers in accordance with current waste management laws.

### PROCESSING

**BASE: EH196R PAGEL - EPOXY RESIN GROUT** is suitable for all mineral bases. The concrete base must be firm, dry, fine-grained and bondable. It should be prepared by blasting with solid blast materials, shot or chamber blasting until the surface has the required bending strength and the grain structure is revealed. The surface bending strength must be maintained (average > 1.5 N/mm²). The residual moisture of the concrete base must not exceed 4% and must be at least 3°C above dew point temperature and the concrete base protected against rising damp. See also the DBV Data Sheet "Utilisation of Reactive Resins in Concrete Constructions, Part 2: Bases".

**ADHESION LAYER:** An adhesion layer is not normally needed. For difficult and very porous bases we recommend applying a primer coat of **EH1 PAGEL - EPOXY RESIN** (see technical specifications).

**MIXING:** The components resin + filler (A) and hardener (B) are delivered in a container in the correct ratio for mixing. Add all the hardener to component A and mix thoroughly with a mechanical mixer at max. 200 rev/min (slow drill with stirrer). Avoid mixing in air. After c. 3-5 minutes mixing pour into clear container and mix again thoroughly. Allow to stand for 5 minutes before using to allow the trapped air to escape.

**POURING:** Pour the epoxy resin grout in a continuous stream into the prepared formwork coated with a separating agent until the required filling height is reached.

**HARDENING:** When handling reactive plastics the temperature of the structural part is very important as well as the ambient temperature. At higher ambient temperatures the chemical reaction times are speeded up, at low temperatures they are delayed. For the reactive plastic to harden fully, the average temperature of the base must be higher than the lowest minimum temperature.

**CLEANING:** Clean tools and equipment with **EPOXY RESIN THINNER**.

The information provided in this leaflet, is supplied by our consulting service and is the end result of exhaustive research work and extensive experience. They are, however, without liability on our part, in particular with regard to third parties proprietary rights, and do not relieve the user of the responsibility for verifying that the products and processes are suitable for the intended application. The data presented was derived from tests under normal climate conditions according to DIN 50014 and mean average values and analysis. Deviations are possible when delivery takes place. Given that recommendations may differ from those shown in this leaflet written confirmation should be sought. It is the responsibility of the purchaser to ensure they have the latest leaflet issue and that its contents are current. Our customer service staff will be glad to provide assistance at any time. We appreciate the interest you have shown in our products. This technical data sheet supercedes previously issued information. Please find the latest leaflet issues at [www.pagel.com](http://www.pagel.com).



### PES [UK] Limited

UNIT 1 WATLING CLOSE SKETCHLEY MEADOWS BUSINESS PARK  
HINCKLEY LEICESTERSHIRE · GB · LE10 3EZ  
TEL. +44 [0]1455 251251 FAX: +44 [0]1455 251252  
WWW.PESUKLTD.COM · E-MAIL: SALES@PESUKLTD.COM

**SPEZIAL-BETON GMBH & CO.KG**  
WOLFSBANKRING 9 · 45355 ESSEN · GERMANY  
TEL. +49 201 68504-0 · FAX +49 201 68504-31  
INTERNET [WWW.PAGEL.COM](http://WWW.PAGEL.COM) · E-MAIL [INFO@PAGEL.COM](mailto:INFO@PAGEL.COM)